bluefiber

smart acoustic technology

Product information

bluefiber **pad 50**

Item number	02074-001
Type of nonwoven	Sound-absorbing acoustic pad made of polyester, thermally bonded, without chemical binders. Smoothed surface.
Fiber composition	100% Polyester
Thickness measuring tape	50 mm
Color	grey
Basis weight DIN EN ISO 9073	2500 g/m²
Standard format	1,25 m x 2,48 m
Packaging unit	box
Quantity per unit	22 pads

This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-01

bluefiber

smart acoustic technology

Product information

bluefiber **pad 50**

	without airgap to the reverberation room floor	50 mm airgap to the reverberation room floor	200 mm airgap to the reverberation room floor
Weighted sound absorption coefficient DIN EN ISO 11654	A I α_w = 0,90	A I α_w = 1,00	A I α_w = 1,00
NRC ASTM C423	0,90	0,95	0,95
SAA ASTM C423	0,89	0,96	0,97

Specific flow resistance DIN EN ISO 9053-1	650 Pa s/m
Air flow resistivity DIN EN ISO 9053-1	13,0 kPa s/m²

Sound absorption in the reverberation room according to DIN EN ISO 354



This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-01

Product information

bluefiber **pad 50**

	classification	assembly situation
Flame resistance DIN EN 13501-1	B – s1, d0	in free standing/free hanging configuration, with a distance of at least 80 mm to other plane building materials, butted joints not permissible

The classification depends on the specific assembly situation. Performances with different assembly situations as described can change the reaction to fire and the qualified FR classification.

	German AgBB (2021)	French VOC class A+	Belgian VOC-regulation
Emissions DIN EN 16516	✓	✓	✓

Resistance against fungi & bacteria DIN EN ISO 846 – procedures A and C	inert to fungal and bacterial growth

This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-01

bluefiber

smart acoustic technology

Product information

bluefiber **pad 50**

Thermal resistance (R) (10 °C) tested in accordance with DIN EN 12667	1,5 m² K/W

Thermal conductivity λ (10 °C) tested in accordance with DIN EN 12667	0,034 W/(m·K)

Light reflectance value (at standard illuminant D65) BS 8493	26,3 %
Gloss level GU DIN EN ISO 2813	1,5

Color fastness to artificial light DIN EN ISO 105-B02	grade > 6

This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-01