

Product information

bluefiber panel I.12

Item number	02058-001
Type of nonwoven	Sound-absorbing acoustic panel made of polyester, thermally & mechanically bonded, without chemical binders. Smoothed surface
Fiber composition	100% Polyester
Performance type	panel I
Thickness caliper	12 mm
Color	warm white
Basis weight DIN EN ISO 9073-1	1000 g/m ²
Standard format	2,07 m x 3,07 m
Packaging unit	pallet
Quantity per packaging unit	94 panels

This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-04


Product information

bluefiber panel I.12

	without air-gap to the reverberation room floor	200 mm air-gap to the reverberation room floor
Weighted sound absorption coefficient DIN EN ISO 11654	D $\alpha_w = 0,30$ (H)	B $\alpha_w = 0,80$
NRC ASTM C423	0,40	0,70
SAA ASTM C423	0,38	0,73

Specific flow resistance DIN EN ISO 9053-1	232 Pa s/m
Length-related flow resistance DIN EN ISO 9053-1	19,3 kPa · s/m ²

Sound absorption in the reverberation room according to DIN EN ISO 354



This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-04

Product information

bluefiber panel I.12

	classification	assembly situation
Flame resistance DIN EN 13501-1	B – s1, d0 equivalent to B – s2, d0 when used in Germany*	in free standing/free hanging configuration, with a distance of at least 80 mm to other plane building materials, butted joints permissible
The classification depends on the specific assembly situation. Performances with different assembly situations as described can change the reaction to fire and the qualified FR classification.		
* new regulation for s1 according to MVV TB 2023/1, annex 4 – table 1.2: TSP _{600s} ≤ 35 m²		

	German AgBB (2024)	French VOC class A+	Belgian VOC-regulation
Emissions DIN EN 16516	✓	✓	✓

Resistance against fungi & bacteria DIN EN ISO 846 – procedures A and C	inert to fungal and bacterial growth
---	--------------------------------------

This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-04

Product information

bluefiber panel I.12

	test result	test conditions
Bending stiffness (force at deflection 10 mm) tested in accordance with DIN EN ISO 178	6 N	support span: 450 mm width pressure fin: 50 mm sample size: 75 mm x 500 mm test speed: 100 mm/min
Ball indentation hardness surface (force at indentation depth 5 mm) tested in accordance with DIN EN ISO 2039-1	80 N	ball diameter: 20 mm sample size: 100 mm x 100 mm ball position: surface centered test speed: 100 mm/min
Ball indentation hardness edge (force at indentation depth 5 mm) tested in accordance with DIN EN ISO 2039-1	60 N	ball diameter: 20 mm sample size: 100 mm x 100 mm ball position: cut edge centered test speed: 100 mm/min
Thermal resistance (R) (10 °C) tested in accordance with DIN EN 12667	0,37 m² K/W	
Light reflectance value (at standard illuminant D65) BS 8493	86,0 %	
Gloss level GU DIN EN ISO 2813	1,4	
Color fastness to artificial light DIN EN ISO 105-B02	grade ≥ 6	

This information has been prepared with reasonable care and diligence as usual in the course of legal communication. Sandler provides no warranties as to the completeness of the information. The properties mentioned are typical values and shall not be deemed agreed quality features. Deviations from the information provided with regard to packaging, storage or delivery may result in product alterations. Processors as well as users shall be obliged to use the product in accordance with the applicable laws and regulations. On an individual basis test certificates may be requested. This data sheet may be updated without prior notice. Thus, a valid data sheet is to be requested prior to each construction project. Failure to do so shall not be at our expense.

SA 2026-04